



KAPCI
COATINGS

Technical Data Sheet

Issue date June 2021

for professional use only

Kapci 222 Underbody





Product description

Kapci 222 is a 1K underbody product based on modified alkyd resin designed to protect car underbody from corrosion as well body floor and other metal parts. Kapci 222 gives anticorrosion properties, excellent adhesion and chemical resistance.

Substrates

Kapci 222 undercoat should be applied over rust free and degreased bare metal. For longer resistance to corrosion, it is recommended to apply an anticorrosive primer prior to overcoating with Kapci 222.

Application

	Thoroughly degrease the surface. For steel use Kapci 606 degreaser for metal.
	Mixing ratio by weight: Add 20% Kapci 525 NC thinner and mix well.
	Use special underbody (UB) gun for underbody products. Nozzle: 6-8mm; Pressure: 4-5 bar Apply 1-2 coats.
	Air dry at 20°C: Dry to handle: 3-4h Hard dry: 24h

Health and Safety

1. For full Health and Safety information refer to the Material Safety Data Sheet (MSDS).
2. Observe the precautionary notices displayed on the container.
3. Goggles and suitable protective equipment must be worn while using these products.
4. Good ventilation must be provided in the working environment.

IMPORTANT NOTE: These TDS are for information purposes only without any obligation as we do not have control over the quality and conditions of the surface or application.